



Maxxon® Commercial MVP Two-Part Epoxy is a 100% solids epoxy coating specially designed to protect underlayments and floor coverings from the damaging effects of moisture vapor emitted through concrete slabs.

- Minimizes environmental impact with zero VOCs
- Outstanding performance with a perm rating of less than 0.10
- Protects up to 100% RH, 25 lbs MVER and a pH of 14
- Fast cure formulation in as little 4 hours
- Low viscosity promotes superior adhesion

WHERE TO USE

Application
Commercial construction.

Subfloor

Interior concrete subfloors below, on or above grade.

25 LBS



MOISTURE PROTECTION IN JUST ONE COAT.

Protect floors from moisture-related issues with Maxxon Commercial MVP Two-Part Epoxy. Designed for use over concrete subfloors with pH levels up to 14 and high moisture levels - up to 100% RH and 25 lbs MVER. Its excellent substrate-wetting capabilities promote penetration and adhesion. Use it in renovating old slabs or with new concrete.

PRODUCT INFORMATION

MVER (ASTM F1869)	Up to 25 lbs/1,000 ft ² (11.3 kg/92.9 m ²)
RH (ASTM F2170)	Up to 100%
Permeance (ASTM E96)	12 mils (125 ft² per gallon): 0.01
Alkalinity Resistance	Up to 14 pH
VOCs	0 g/l
Color	Amber, dries translucent
Tensile Strength (ASTM D638)	5,500 psi (38 MPa)
Installation Temperature	45-95°F (7-35°C)
Working Time	20 minutes at 77 °F (25 °C)
Curing Time	4 hours at 77 °F (25 °C)
Coverage	One kit covers 375 ft² (34.8 m²); 125 ft² /gal (3.06 m²/L)

3 GAL KIT A Part #13043 MAXXON **MVP Two**

INSTALLATION & LIMITATIONS

See technical data sheet available at Maxxon.com for limitations and complete installation instructions.

PACKAGING

3 gal (11.4 L) kit with 2 gal (7.6 L) Part A and 1 gal (3.8 L) Part B

PRO TIP

When starting the project, tape off the square footage for the first unit to gauge coverage.

Maxxon Corporation

920 Hamel Road PO Box 253 Hamel, Minnesota 55340 800-238-8461

maxxon.com

info@maxxon.com



f @Maxxon.Corporation



maxxon-corporation